

111.3 - Ore Bioleaching Substrate (powder form)

This RM is for use as a bioleaching substrate and for testing bioleaching rates. The material consists of pyrite from New Mexico. *Thiobacillus ferrooxidans* was used in the determinations.

Technical Contact: robert.vocke@nist.gov

PLEASE NOTE: The tables are presented to facilitate comparisons among a family of materials to help customers select the best SRM for their needs. For specific values and uncertainties, the certificate is the only official source.

SRM	8455
Description	Pyrite Ore
Unit Size	(100 g)
Bioleaching Rate (in mgFe/L/hr)	12.4